



Tel: +44 (0) 1942 265 700 Fax: +44 (0) 1942 670 788 www.intertek.com/consumergoods

FLAMMABILITY TEST REPORT

Report No.: LEHTX00930633 **Date Received:** 06/01/17 **Date Tested:** 10/01/17 1st Date Issued: 10/01/17

Retype Issued: 11/01/17 Retype

BUTE FABRICS LTD Company Name & Address:

4 BARONE ROAD **ROTHESAY** ISLE OF BUTE PA20 ODP

Contact Name: S MCGROARTY

Sample Details

135915/3123 Order No.: Description: Woven Fabric Ref/Style No.: CF944 /Coast

Colour: Grey Nimbus Quality: Supplier: Bute Batch No .: 29752/04 End Use: Curtains

Quoted Fibre Composition: 100% Pure New Wool

Retailer: Not stated

Sample Description: Grey coloured woven fabric

Test Method	Pre Treatment	Flammability Performance Requirement	Result
BS 5867: Part 2: 2008	The sample was tested without any form of cleansing or wetting procedure as requested by the customer.	Туре В	PASS

Note: In accordance with clause 7 of BS 5867: Part 2: 2008 a fabric for which compliance with the requirements of this standard is claimed shall be supplied with the following information, the manufacturer's name, trademark or other identifying mark, the statement 'Flammability complies with the requirements of BS 5867: Part 2 Type B' and instructions on any special precautions to be taken concerning care (including cleansing) of the product, preferably using an appropriate care labelling symbol in accordance with BS EN ISO 3758 and taking account of the durability procedure used in this test.

Fabrics which are claimed to be treated with a non-durable flame-retardant finish may be tested without any form of cleansing or wetting procedure prior to testing if agreed between the parties involved. BS 5867: Part 2: 2008 states that if the fabric tested has not been subjected to any form of cleansing or wetting procedure prior to testing due to the fabric being treated with a non-durable flame retardant finish it is important that the fabric be clearly labelled as follows:

WARNING: IF WETTED IN ANY WAY IT IS ESSENTIAL TO RE-TREAT THE FABRIC TO MEET FLAMMABILITY

REQUIREMENTS. Or:

WARNING : WETTING IN ANY WAY MIGHT REMOVE THE FIRE RESISTING QUALITIES OF THE FABRIC

STEVEN OWEN ANDREW HALLETT **CAROLE SPOWART** (Chemical Technologist)

(Flammability Team Leader) (Flammability Technician)

SIMON CHEE (Operations Manager)





Report No.: LEHTX00930633 Retype Page 1 of 2





Tel: +44 (0) 1942 265 700 Fax: +44 (0) 1942 670 788 www.intertek.com/consumergoods

FLAMMABILITY TEST REPORT

Test Specification

Test Method: BS 5867: Part 2: 2008 Type B using BS EN ISO 15025:2002

(With the modifications from clause 6.3.2 of BS 5867: Part 2: 2008).

Ignition Source: 25mm horizontal reach Butane gas flame

Ignition Type: Surface Flame Application Time: 15±1 seconds Sample Size: 200 x 160mm

Side Tested: Face

Pre-Treatment / Durability Procedure

None

Conditioning

Prior to Testing: At least 24 hours in an atmosphere having a temperature of 20±2°C. and a relative

humidity of 60±5%

At Time of Testing: Temperature between 15°C & 30°C. Relative humidity between 20% & 65%

Report of tests carried out in accordance with BS EN ISO 15025:2002. The results may not apply to situations where there is

restricted air supply or prolonged exposure to large sources of intense heat as in a conflagration.

Sample No./	Duration of	Duration of	Flaming debris	Flame to edge	Hole to edge	Maximum damaged length (mm)	
Direction	flaming (Secs)	afterglow (Secs)				Horizontal	Vertical
1. Length ↑	0.0	0.0	No	No	No	26	60
2. Length ↓	0.0	0.0	No	No	No	25	60
3. Length ↑	0.0	0.0	No	No	No	25	60
4. Width →	0.0	0.0	No	No	No	25	58
5. Width ←	0.0	0.0	No	No	No	24	55
6. Width →	0.0	0.0	No	No	No	23	68

Conclusions

When tested without any form of cleansing or wetting procedure the sample meets the flammability performance requirements of BS 5867: Part 2: 2008 Type B. PASS.

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have <u>aimed</u> to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or willful misconduct.





